

Technical Data Sheet

Corkcomfort Glue-down WRT

Dimensions Available

600x300x4 mm - 23-5/8x11-13/16x5/32 inches

Domestic	EN ISO 10874:2012	Class	23	
Commercial	EN ISO 10874:2012	Class	31	
General properties - EN 12104				
Standard - Test Method	Unit	Specification		
Dimensions	EN 427	mm	≤ 0,2% up to 1,0 mm max.	
Overall thickness	EN 428	mm	0; +0,25	
Squareness and Straightness: ≤ 400mm > 400mm	EN 427	mm	≤ 0,5 ≤ 1,0	
Apparent density	EN 672	Kg/m ³	≥ 95% of nominal value (450)	
Mass per unit area	EN 430	g/m ²	Nominal value (2000) ± 10 %	
Dimensional stability	EN 434	%	≤ 0,4	
Curling after exposure to heat	EN 434	mm	≤ 6	
Moisture content	EN 12105	%	2,5 - 6	
Classification Properties - EN 12104				
Overall thickness	EN 428	mm	≥ 4,0	
Apparent density	EN 672	Kg/m ³	≥ 450	
Residual indentation	EN 433	mm	≤ 0,40	
Safety properties - EN 14041				
Fire resistance	EN 13501-1	Class	Dfl s1	
Slip Classification	EN 13893	Class	DS	
Formaldehyde emission	DIN EN 717-1	Class	E1	
Electrical behaviour	EN 1815	KV	Not Antistatic	
Content pentachlorophenol (PCP)	CEN/TR 14823 (ihd-W 409)	mg/Kg	PCP Free	
Optional properties				
Stains Resistance	EN 423 (a)	Grade	Grade 0 (b)	
Thermal resistance	EN 12667	(m ² K)/W	R ≤0,150	
Impact sound reduction	ISO 140-8	dB (Δ L _w)	12	
Step sound	NF S 31 - 074	dB (L _{n,e,w})	65	
Gloss	Glossmeter (60°)	Degrees Gardner(°G)	12 ± 3°	

(a) The following products were tested: Desinfectant, C₂H₅OH, NH₄OH, Citric Acid, Iodine

(b) Grade 0 - Unchanged / Grade 1 - Very little change / Grade 2 - Little change / Grade 3 - Change / Grade 4 - Strong Change

www.wicanders.com

