



Technical Data Sheet

Corkcomfort Glue-down Sanded

Dimensions Available

600x300x4 mm - 23-5/8x11-13/16x5/32 inches

Domestic	EN ISO 10874:2012	Class	23 (a)	
Commercial	EN ISO 10874:2012	Class	31 (b)	
General properties - EN 12104				
General properties - EN 12104	Standard - Test Method	Unit	Specification	
Dimensions	EN 427	mm	≤ 0,2% up to 1,0 mm max.	
Overall thickness	EN 428	mm	0; +0,25	
Squareness and Straightness: ≤ 400mm > 400mm	EN 427	mm	≤ 0,5 ≤ 1,0	
Apparent density	EN 672	Kg/m ³	≥ 95% of nominal value (450)	
Dimensional stability	EN 434	%	≤ 0,4	
Curling after exposure to heat	EN 434	mm	≤ 6	
Moisture content	EN 12105	%	2,5 - 6	
Classification properties - EN 12104				
Residual indentation	EN 433	mm	≤ 0,40	
Safety properties - EN 14041				
Formaldehyde emission	DIN EN 717-1	Class	E1	
Electrical behaviour	EN 1815	KV	Not Antistatic	
Content pentachlorophenol (PCP)	CEN/TR 14823 (ihd-W 409)	mg/Kg	PCP free	
Optional properties				
Thermal resistance	EN 12667	m ² K/W	R ≤ 0,150	
Impact sound reduction	ISO 140-8	dB (Δ L _w)	12	
Step sound	NF S 31 - 074	dB (L _{sub,eq})	65	

(a) Must be varnished on-site with minimum 3 coats of w-700 or w-2000 or another recommended varnish

(b) Must be varnished on-site with minimum 3 coats of w-2000 or another recommended varnish for this level of use (see recommendation table in the packaging)

www.wicanders.com

